

## CLAIMS

1. A multi-layer heat-shrinkable film comprising at least a first outer heat-sealing layer (a) comprising one or more polyolefins; a second outer abuse layer (b) comprising a polyamide with melting point  $\geq 175^{\circ}\text{C}$ ; and an intermediate gas barrier layer (c) comprising PVDC.
2. The multi-layer heat-shrinkable film of claim 1 wherein the polyamide of the outer abuse layer (b) has a melting point of from about  $175^{\circ}\text{C}$  to about  $250^{\circ}\text{C}$ ; preferably of from about  $180^{\circ}\text{C}$  to about  $240^{\circ}\text{C}$ ; more preferably of from about  $185^{\circ}\text{C}$  to about  $230^{\circ}\text{C}$ ; and still more preferably of from about  $188^{\circ}\text{C}$  to about  $225^{\circ}\text{C}$ .
3. The multi-layer heat-shrinkable film of claim 2 wherein the polyamide of the outer abuse layer (b), with a melting temperature of from about  $188^{\circ}\text{C}$  to about  $225^{\circ}\text{C}$ , is selected from the group consisting of copolyamides 6/12, copolyamides 6/66, polyamide 6 copolymers (modified polyamide 6) comprising less than 5 %, preferably less than 4 %, and even more preferably less than 3 % by weight of an aromatic co-monomer, copolyamides of polyamide 6 and a partially aromatic polyamide, and terpolyamides based on polyamide 6, polyamide 11, and polyamide 66.
4. The multi-layer heat-shrinkable film of claim 2 wherein the outer abuse layer (b) comprises at least 50 % by weight and preferably at least 60 % by weight of one or more polyamides with a m.p.  $\geq 175^{\circ}\text{C}$ , blended with an ethylene-vinyl alcohol copolymer.
5. The multi-layer heat-shrinkable film of claim 4 wherein the amount by weight of EVOH in the outer abuse layer (b) with respect to the overall weight of the layer is comprised between about 3 and about 40 % by weight, preferably between about 5 and about 35 % by weight, and even more preferably between about 10 and about 30 %.
6. The multi-layer heat-shrinkable film of claim 1 wherein the heat-sealing layer (a) comprises a single polyolefin or a blend of two or more polyolefins with melting temperature  $< 140^{\circ}\text{C}$ , preferably  $< 130^{\circ}\text{C}$ , and more preferably comprised between  $80^{\circ}\text{C}$  and about  $128^{\circ}\text{C}$ .

7. The multi-layer heat-shrinkable film of claim 6 wherein the heat-sealing layer (a) comprises heterogeneous or homogeneous ethylene-(C<sub>4</sub>-C<sub>8</sub>)- $\alpha$ -olefin copolymers having a density  $\leq 0.915$  g/cm<sup>3</sup>, blends thereof with minor amount of polyethylene homopolymers, ethylene-vinyl acetate copolymers, ethylene-acrylic or methacrylic acid copolymers including ionomers, blends of heterogeneous or homogeneous ethylene-(C<sub>4</sub>-C<sub>8</sub>)- $\alpha$ -olefin copolymers having a density from about 0.915 g/cm<sup>3</sup> to about 0.930 g/cm<sup>3</sup> with ethylene-vinyl-acetate copolymers or ethylene-alkyl (meth)acrylate copolymers, ethylene-propylene-butene ter-polymers, ethylene-alkyl acrylate-maleic anhydride ter-polymers.
8. The multi-layer heat-shrinkable film of claim 7 wherein the heat-sealing layer (a) comprises a heterogeneous or homogeneous ethylene-(C<sub>4</sub>-C<sub>8</sub>)- $\alpha$ -olefin copolymer having a density  $\leq 0.915$  g/cm<sup>3</sup>, and preferably a heterogeneous or homogeneous ethylene-(C<sub>4</sub>-C<sub>8</sub>)- $\alpha$ -olefin copolymer having a density comprised between about 0.895 g/cm<sup>3</sup> and about 0.912 g/cm<sup>3</sup>.
9. The multi-layer heat-shrinkable film of claim 1 in the form of a seamless tubing wherein the outer heat-sealing layer (a) is the innermost layer of the tube.
10. A container obtained from a multi-layer heat-shrinkable film comprising at least a first outer heat-sealing layer (a) comprising one or more polyolefins; a second outer abuse layer (b) comprising a polyamide with melting point  $\geq 175$  °C; and an intermediate gas barrier layer (c) comprising PVDC, by a welding involving the outer heat-sealing layer (a), whereby said outer layer (a) is the inside layer of the container and the outer abuse layer (b) is the outside layer of the container.

Add  
AI